

Tork Premium Reinigungstücher 510 blau Handy Box



Artikel: 510271

System: W7 – Handy Box System

Lagen: 1

Farbe: Blau

Breite entfaltet: 38.5 cm

Länge entfaltet: 42.8 cm

Länge gefaltet: 10.8 cm

Bedruckt: Nein

Geprägt:

Produkteigenschaften

- Das dünne Material ermöglicht auch die problemlose Reinigung von engen Stellen
- Hohe Reinigungsleistung in trockenem wie in nassem Zustand
- ISEGA-zertifiziert: für den kurzzeitigen Kontakt mit Lebensmitteln geeignet
- Handy Box

Versanddaten

Verbrauchseinheit:

EAN: 7322540057447

Stück: 300

Höhe: 238 mm

Breite: 236 mm

Länge: 395 mm

Volumen: 22.2 dm³

Nettogewicht: 2719 g

Bruttogewicht: 3064 g

Transporteinheit:

EAN: 7322540057454

Stück: 300

Verbrauchseinheiten: 1

Material: Carton

Höhe: 238 mm

Breite: 236 mm

Länge: 395 mm

Volumen: 22.2 dm³

Nettogewicht: 2.72 kg

Bruttogewicht: 3.06 kg

Umweltschutz

Content

Chemical pulp, Polypropene, Polyester, Chemicals

Material

Chemical pulp Chemical pulp is produced either from softwood or hardwood. The wood chips are boiled together with chemicals and the major part of the lignin is removed. Chemical pulp is bleached in order to achieve a clean, bright and strong product, but also to increase the hygienic and absorbent qualities. There are two major bleaching methods: ECF (elementary chlorine free) and TCF (totally chlorine free). ECF is based on oxygene, chlorine dioxide and hydrogen peroxide. TCF is based on hydrogen peroxide and ozone. ECF is used in this product.

Polypropene Polypropene fibre is produced from polypropene resin. The resin is melted in an extruder and spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Polyester** Polyester fibre is produced from terephthalic acid and ethyleneglycol, which react through condensation to polyester resin. The molten resin is spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Chemicals** Both functional and process chemicals are used. The functional chemical used is wet strength agent. The wet strength agent is a polyamide (from polyamidine/epichlorhydrine polymer) with a very high affinity to the fibre. Process chemical used is a surfactant.

Production

This product is produced at Suameer mill, The Netherlands, and certified according to ISO 9001:2000, ISO 14001 and EMAS.

Destruction

This product is mainly used for industrial processes and hence it will be contaminated with different substances. This will determine how the used product will be destroyed. The product itself is suitable for incineration. Contact local authorities before destruction.