

## Technical product specification

<b>Product name</b>	<b>semperguard latex comfort</b>	<b>Version / Index no:</b>
<b>Spec code</b>	<b>LCF/LOF-050NA-N-3CZ</b>	semperguard latex comfort_LCF/LOF-050NA-N-3CZ_Version A_November 2024_EN
<b>Date of issue</b>	<b>14.11.2024</b>	

### General information

<b>Type</b>	single use examination and disposable protective glove, non sterile
<b>Labelling</b>	information printed on dispenser box
<b>Shape</b>	ambidextrous - straight fingers
<b>Material</b>	Natural Rubber Latex (NRL)
<b>Colour</b>	natural white
<b>Inside</b>	powder free
<b>Outside</b>	no treatment
<b>Cuff / surface</b>	rolled cuff / finger textured
<b>Shelf life</b>	3 years
<b>Available sizes</b>	XS (5-6) S (6-7) M (7-8) L (8-9) XL (9-10)

### Dimensions, physical properties and biocompatibility

<b>Glove length</b>	median $\geq 240$ mm (according to EN 455-2)
<b>Minimum wall thickness</b>	<b>at finger</b> 0.18 mm (double measured) / 0.09 mm (single measured) <b>at palm</b> 0.16 mm (double measured) / 0.08 mm (single measured) <b>at cuff</b> 0.12 mm (double measured) / 0.06 mm (single measured)
<b>Glove width</b>	according to EN 455-2: median XS $\leq 80$ mm, S $80 \pm 10$ mm, M $95 \pm 10$ mm, L $110 \pm 10$ mm, XL $\geq 110$ mm
<b>Force at Break</b>	median $\geq 6$ N (during shelf life according to EN 455-2)
<b>Tensile Strength</b>	min. 14 MPa after aging (according to ASTM D3578)
<b>Elongation at Break</b>	min. 500% after aging (according to ASTM D3578)
<b>Residual powder / Powder content</b>	$\leq 2$ mg (according to EN 455-3)

### Performance requirement and inspection level

<b>Freedom from holes (Barrier)</b>	AQL $\leq 1.5$ (as per EN 455-1, sampling in accordance with ISO 2859-1, G-1)
-------------------------------------	--

### Standards, guidelines & quality certificates

<b>Quality certification</b>	ISO 9001, ISO 13485
<b>Conformity to regulations</b>	- Medical Device Regulation (EU) 2017/745: Class I - PPE Regulation (EU) 2016/425: Category III - Regulation (EC) 1935/2004 on Food Contact Materials
<b>Conformity to standards</b>	EN ISO 21420, EN ISO 374-1 (Type C), EN ISO 374-2, EN 16523-1, EN ISO 374-4, ISO 374-5, EN 455-1, EN 455-2, EN 455-3, EN 455-4, ISO 2859-1, ASTM D3578 (except stress at 500% elongation), ASTM F1671/F1671M

## Technical product specification

<b>Product name</b>	<b>semperguard latex comfort</b>	<b>Version / Index no:</b>
<b>Spec code</b>	<b>LCF/LOF-050NA-N-3CZ</b>	semperguard latex comfort_LCF/LOF-050NA-N-3CZ_Version A_November 2024_EN
<b>Date of issue</b>	<b>14.11.2024</b>	

### Instructions and additional statements

#### Storage instruction




Store in original packaging in a dry and dark place at 10° C to 30° C. Refer to guidelines of storage of rubber products as described in ISO 2230:2002. Ensure that storage area is kept cool, dry and dust free, avoid ventilation and storage close to photocopy equipment. Copper ions discolour the glove. Protect gloves against ultraviolet light sources, such as sunlight and oxidizing agents. Storage above 30° C will lead to accelerated aging and should be avoided.

#### Cautionary statement and ingredient information

This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses. Contains potential Type IV chemical allergens (Dithiocarbamate types, Zinc-mercaptobenzothiazol). For further information, a list of substances contained in the glove is available upon request. E-Mail: [sempermed@harpsglobal.com](mailto:sempermed@harpsglobal.com)

#### Medical device vigilance and reporting system

According to the official reporting criteria of the Medical Device Regulation, incidents caused by examination gloves must be reported immediately to our Medical Device Reporting team. E-Mail: [sempermed.complaints@harpsglobal.com](mailto:sempermed.complaints@harpsglobal.com)

 A. Wöss <i>Sr Vice President Sales</i>	 B. Sebauer <i>Head of Quality Management and Regulatory Affairs</i>	 M. Schirmbrandt <i>Product Management</i>
--	---	--

#### Remark

Replaces all previous versions.  
All standards references refer to the date of document issue.